Test Report Number: GZHH00474979

Applicant: FIBERPLAST BIOBASED BV
DE KLETTEN 10 9206 BA DRACHTEN
FRIESLAND THE NETHERLANDS

Date: Nov 25, 2022

Attn: GARY DING

Sample Description:

One (1) submitted sample said to be **Mega Deck 190m x 42mm**

P. O. No.	:	Mega Deck 190m x 42mm
Buyer	:	Fiberplast Biobased BV
Manufacturer	:	Binzhou Sunshien WPC Co.,Ltd
Country of Destination	:	Holland
Country of Origin	:	China
Date Sample Received	:	Nov 15, 2022
Testing Period	:	Nov 15, 2022 to Nov 25, 2022



****

Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

****

To be continued

Intertek Testing Services Shenzhen Limited, Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
111, Huichuang Kongjian, TCL Cultural Industrial Park, No.69, Guangpu Road, Huangpu District, Guangzhou, Guangdong, China. / Block E, No.7-2 Caipin Road, Science City, GETDD, Guangzhou.
广州市黄埔区光谱西路 69 号 TCL 文化产业园汇创空间 111 室/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com

Test Report Number: GZHH00474979

Conclusion:

Tested sample	Test item	Result
Submitted sample	Fire Classification Test on WPC Decking - As per EN 13501-1: 2018	See test conducted

****

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines

Victor T.J. Wang
Assistant General Manager

Intertek Testing Services Shenzhen Limited, Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
111, Huichuang Kongjian, TCL Cultural Industrial Park, No.69, Guangpu Road, Huangpu District, Guangzhou, Guangdong, China. / Block E, No.7-2 Caipin Road, Science City, GETDD, Guangzhou.
广州市黄埔区光谱西路 69 号 TCL 文化产业园汇创空间 111 室/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com

Test Report Number: GZHH00474979

Tests Conducted

1 Fire Classification Test on WPC Decking

As per EN 13501-1:2018, the tested samples were subjected to the following tests.

Sample description: WPC Decking

Sample thickness: 40mm

Initial inspection: No any damage was found

Executive summary:

No.	Test item			Test method	Standard's requirement		Test result	Conclusion
1	Critical heat flux			EN ISO 9239-1: 2010	B_{fl}	≥8.0kW/m^2	≥11kW/m^2	Pass
2	Flammability	Surface flame attack (Exposure = 15 s)	Flame spread within 20s	EN ISO 11925-2:2010+AC: 2011		⩽150mm	20mm	Pass
3	Smoke production			EN ISO 9239-1:2010	s1	⩽ 750%×min	56.3%×min	Class: s1
					s2	Not s1		
Conclusion	**EN 13501-1:2018 Fire classification of construction products and building elements - Part 1: Classification using data from reaction to fire tests : B_{fl} - s1**							
Remark	The test results relate to the behavior of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.							

Intertek Testing Services Shenzhen Limited, Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
111, Huichuang Kongjian, TCL Cultural Industrial Park, No.69, Guangpu Road, Huangpu District, Guangzhou, Guangdong, China. / Block E, No.7-2 Caipin Road, Science City, GETDD, Guangzhou.
广州市黄埔区光谱西路 69 号 TCL 文化产业园汇创空间 111 室/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com

Annex A

Classes of reaction to fire performance for floorings

Class	Test method(s)	Classification criteria	Additional classification
$A1_{fl}$	EN ISO 1182 [a] and	$\Delta T \leq 30$ °C; and $\Delta m \leq 50$ %; and $t_f = 0$ (i.e. no sustained flaming)	-
	EN ISO 1716	*PCS* ≤ 2,0 MJ/kg [a] and *PCS* ≤ 2,0 MJ/kg [b] and *PCS* ≤ 1,4 MJ/m^2 [c] and *PCS* ≤ 2,0 MJ/kg [d]	-
$A2_{fl}$	EN ISO 1182 [a] or	$\Delta T \leq 50$ °C and $\Delta m \leq 50$ % and $t_f \leq 20$ s	-
	EN ISO 1716 and	*PCS* ≤ 3,0 MJ/kg [a] and *PCS* ≤ 4,0 MJ/m^2 [b] and *PCS* ≤ 4,0 MJ/m^2 [c] and *PCS* ≤ 3,0 MJ/kg [d]	-
	EN ISO 9239-1 [e]	Critical flux [f] ≥ 8,0 kW/m^2	Smoke production [g]
B_{fl}	EN ISO 9239-1 [e] and	Critical flux [f] ≥ 8,0 kW/m^2	Smoke production [g]
	EN ISO 11925-2 [h]: Exposure = 15 s	*F*s ≤ 150 mm within 20 s	-
C_{fl}	EN ISO 9239-1 [e] and	Critical flux [f] ≥ 4,5 kW/m^2	Smoke production [g]
	EN ISO 11925-2 [h]: Exposure = 15 s	*F*s ≤ 150 mm within 20 s	

Intertek Testing Services Shenzhen Limited, Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
111, Huichuang Kongjian, TCL Cultural Industrial Park, No.69, Guangpu Road, Huangpu District, Guangzhou, Guangdong, China. / Block E, No.7-2 Caipin Road, Science City, GETDD, Guangzhou.
广州市黄埔区光谱西路 69 号 TCL 文化产业园汇创空间 111 室/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com

Test Report Number: GZHH00474979

Tests Conducted

Class	Test method(s)	Classification criteria	Additional classification
D_{fl}	EN ISO 9239-1 [e] and	Critical flux [f] ≥ 3,0 kW/m^2	Smoke production [g]
	EN ISO 11925-2 [h]: Exposure = 15 s	*F*s≤150mm within 20 s	
E_{fl}	EN ISO 11925-2 [h]: Exposure = 15 s	Fs ≤ 150 mm within 20 s	
F_{fl}	No performance determined		

[a] For homogeneous products and substantial components of non-homogeneous products.

[b] For any external non-substantial component of non-homogeneous products.

[c] For any internal non-substantial component of non-homogeneous products.

[d] For the product as a whole.

[e] Test duration = 30 min.

[f] Critical flux is defined as the radiant flux at which the flame extinguishes or the radiant flux after a test period of 30 min, whichever is the lower (i.e. the flux corresponding with the furthest extent of spread of flame).

[g] **s1** = Smoke ≤ 750 % minutes;

s2 = not s1.

[h] Under conditions of surface flame attack and, if appropriate to the end use application of the product, edge flame attack

****

End of report

*The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band **w** = **U**) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.*

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch. The testing data and result issued by this report are just for scientific research, teaching, internal quality control, product research and development etc. on reference only in the territory of the People's Republic of China.

Intertek Testing Services Shenzhen Limited, Guangzhou Branch
深圳天祥质量技术服务有限公司广州分公司
111, Huichuang Kongjian, TCL Cultural Industrial Park, No.69, Guangpu Road, Huangpu District, Guangzhou, Guangdong, China. / Block E, No.7-2 Caipin Road, Science City, GETDD, Guangzhou.
广州市黄埔区光谱西路 69 号 TCL 文化产业园汇创空间 111 室/广州经济技术开发区科学城彩频路 7 号之二 E 栋(510663)

Tel +8620 8213 9688
Fax +8620 3205 3537
intertek.com.cn
intertek.com